

PUB-N0: JP02003105513A

DOCUMENT-IDENTIFIER: JP 2003105513 A

TITLE: HIGH STRENGTH GALVANIZED STEEL SHEET HAVING EXCELLENT APPEARANCE AND WORKABILITY, AND PRODUCTION METHOD THEREFOR

PUBN-DATE: April 9, 2003

INVENTOR-INFORMATION:

NAME	COUNTRY
<u>FUJITA, NOBUHIRO</u>	
<u>AZUMA, MASASHI</u>	
TAKAHASHI, MANABU	
MORIMOTO, YASUhide	
KUROSAKI, MASAO	
MIYASAKA, AKIHIRO	

ASSIGNEE-INFORMATION:

NAME	COUNTRY
NIPPON STEEL CORP	

APPL-N0: JP2001304036
APPL-DATE: September 28, 2001

INT-CL (IPC): C23C 2/06; C21D 9/46; C22C 18/00; C22C 38/00; C22C 38/12; C22C 38/58; C23C 2/02; C23C 2/40

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a high strength galvanized steel sheet which has suppressed occurrence of unplating, and has excellent appearance and workability, and to provide a production method therefor.

SOLUTION: The high strength galvanized steel sheet having excellent appearance and workability is obtained by providing the surface of a steel sheet containing, by mass, 0.0001 to 0.3% C, 0.001 to <0.1% Si, 0.01 to 3% Mn, 0.001 to 4% Al, 0.001 to 1% Mo, 0.0001 to 0.3% P and 0.0001 to 0.1% S, and the balance Fe with inevitable impurities with a plated layer having a composition containing 0.001 to 3% Mn, 0.001 to 4% Al, 0.0001 to 1% Mo and 5 to 20% Fe, and the balance Zn with inevitable impurities. Provided that the content of Mn in the steel is defined as X (mass%), the content of Si in the steel as Y (mass%), and the content of Si in the plating as Z (mass%), X, Y and Z satisfy the following inequality: $0.6 - (X/18 + Y + Z) \geq 0$ (1).

COPYRIGHT: (C)2003,JP0